

# Liquid Batik

03  
Lemon Yellow

06  
Corn Yellow

10  
Orange

14  
Red

16  
Pink

18  
Lilac

21  
Brilliant Blue

38  
Navy Blue

27  
Green

32  
Brown

40  
Black



## User directions

100 ml colour and 200 g Fixing agent is sufficient for the full strength dyeing of 700 g dry, white, dress free cotton fabric. Exception: 100 ml Black no. 240 is sufficient for 350 g fabric.

## Procedure:

Dissolve 1.000 g table salt in 10 litres 40°C or 60°C hot water, the hottest water gives the darkest colours. Add 100 ml of Liquid Batik Colour. Dissolve 200 g fixing agent in hot water and pour it into the colour bath. Put immediately the weighed, wet, unfolded fabric into the colour bath.

Let the fabric float free in the bath for 30 minutes. Stir regularly to avoid discolorations. After the dyeing the fabric is rinsed in several changes of water and afterwards washed in the machine with soap at 40°C.

Remember to wet the fabric before the dyeing.



ISO 14001:2015

# Schjerning

SINCE 1886 · MADE IN DENMARK

Schjerning Farver A/S  
DK-8400 Ebeltoft  
[www.schjerning.dk](http://www.schjerning.dk)